

This page is mainly introduced the 302 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 302, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels 302

302 Standard Number:		
ITEM	Standard Number	Descriptions
1	A 240/A 240M (2012)	Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications
2	A 313/A 313M (2010)	Stainless Steel Spring Wire
3	A 314 (2008)	Stainless Steel Billets and Bars for Forging
4	A 368 (2009)	Stainless Steel Wire Strand
5	A 473 (2009)	Stainless Steel Forgings
6	A 478 (2008)	Chromium-Nickel Stainless Steel Weaving and Knitting Wire
7	A 479/A 479M (2011)	Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels
8	A 492 (2009)	Stainless Steel Rope Wire
9	A 493 (2009)	Stainless Steel Wire and Wire Rods for Cold Heading and Cold Forging
10	A 511/A 511M (2012)	Seamless Stainless Steel Mechanical Tubing
11	A 554 (2011)	Welded Stainless Steel Mechanical Tubing
12	A 580/A 580M (2012)	Stainless Steel Wire
13	A 666 (2010)	Annealed or Cold-Worked Austenitic Stainless Steel Sheet, Strip, Plate, and Flat Bar
14	A 959 (2011)	Standard Guide for Specifying Harmonized Standard Grade Compositions for Wrought Stainless Steels
15	SAE AMS-QQ-S-763B (1998)	Steel, Corrosion Resistant, Bars, Wire, Shapes, and Forgings Standard Withdrawn
16	SAE AMS-S-7720A (1997)	Steel, Corrosion-Resistant (18-8) Bars, Wire and Forging Stock (Aircraft Quality)
17	SAE J 405 (1998)	Chemical compositions of SAE wrought stainless steels
18	SAE J 467 (1968)	Special Purpose Alloys

302 Chemical composition(mass fraction)(wt.%)		
Chemical	Min.(%)	Max.(%)
C		0.15
Si		1.00
Mn		2.00
P		0.045
S		0.03

Cr	18.0	19.0
Ni	8.00	10.00

302 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	$Akv \geq$ /J
HBS	123-321	-
HRC	30	-

302 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	$Akv \geq$ /J
HBS	235-268	-
HRC	30	-

302 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

302 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

