

This page is mainly introduced the 00Cr17Ni14Mo2 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 00Cr17Ni14Mo2, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels 00Cr17Ni14Mo2

00Cr17Ni14Mo2 Standard Number:		
ITEM	Standard Number	Descriptions
1	GB 13296 (2007)	Seamless stainless steel tubes for boiler and heat exchanger
2	GB 2270 (1980)	Seamless tubes
3	GB/T 1220 (1992)	Stainless steel bars
4	GB/T 12770 (2002)	Welded stainless steel tubes for machine structures
5	GB/T 12771 (2000)	Welded stainless steel pipes for liquid delivery
6	GB/T 14975 (2002)	Stainless steel seamless tubes for structures
7	GB/T 14976 (2002)	Stainless steel seamless tubes for fluid transport
8	GB/T 3089 (1982)	Thinnest-wall seamless tubes of stainless and acid-resistance steel
9	GB/T 3090 (2000)	Stainless steel small diameter seamless steel tubes
10	GB/T 3280 (2007)	Cold rolled stainless steel sheets and plates
11	GB/T 4226 (2004)	Cold finished stainless steel bars
12	GB/T 4237 (1992)	Hot rolled stainless steel sheets and plates
13	GB/T 4239 (1991)	Cold rolled stainless steel and heat resisting steel strips
14	GB/T 4240 (1993)	Stainless steel wires
15	GB/T 4356 (2002)	Stainless steel wire rods
16	JB 4728 (2000)	Stainless Steel Forgings for Pressure Vessels

00Cr17Ni14Mo2 Chemical composition(mass fraction)(wt.%)		
Chemical	Min.(%)	Max.(%)
C		0.030
Si		1.00
Mn		2.00
P		0.035
S		0.030
Ni	12.00	15.00

Cr	16.00	18.00
Mo	2.00	3.00

00Cr17Ni14Mo2 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	123-321	-
HRC	30	-

00Cr17Ni14Mo2 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta_5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	235-268	-
HRC	30	-

00Cr17Ni14Mo2 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

00Cr17Ni14Mo2 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

