This page is mainly introduced the SUSXM7 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of SUSXM7, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Data Table for Grades Special Alloy SUSXM7

| SUSXM7 Standard Number: |                 |              |  |  |
|-------------------------|-----------------|--------------|--|--|
| ITEM                    | Standard Number | Descriptions |  |  |
|                         |                 | ·            |  |  |

| SUSXM7 Chen | SUSXM7 Chemical composition(mass fraction)(wt.%) |         |  |  |
|-------------|--------------------------------------------------|---------|--|--|
| Chemical    | Min.(%)                                          | Max.(%) |  |  |

| SUSXM7 Physical Properties |         |             |  |  |
|----------------------------|---------|-------------|--|--|
| Tensile strength           | 115-234 | σb/MPa      |  |  |
| Yield Strength             | 23      | σ 0.2 ≥/MPa |  |  |
| Elongation                 | 65      | δ5≥ (%)     |  |  |
| Ψ                          | -       | ψ≥ (%)      |  |  |
| Akv                        | -       | Akv≥/J      |  |  |
| HBS                        | 123-321 | -           |  |  |
| HRC                        | 30      | -           |  |  |

| SUSXM7 Mechanical Properties |         |             |  |
|------------------------------|---------|-------------|--|
| Tensile strength             | 231-231 | σb/MPa      |  |
| Yield Strength               | 154     | σ 0.2 ≥/MPa |  |
| Elongation                   | 56      | δ5≥(%)      |  |
| ψ                            | -       | ψ≥(%)       |  |
| Akv                          | -       | Akv≥/J      |  |
| HBS                          | 235-268 | -           |  |
| HRC                          | 30      | -           |  |

| SUSXM7 Heat Treatment Regime |              |              |              |       |
|------------------------------|--------------|--------------|--------------|-------|
| Annealing                    | Quenching    | Tempering    | Normalizing  | Q & T |
| $\checkmark$                 | $\checkmark$ | $\checkmark$ | $\checkmark$ |       |



| SUSXM7 Range of products |                                             |                               |                                             |                                                                      |
|--------------------------|---------------------------------------------|-------------------------------|---------------------------------------------|----------------------------------------------------------------------|
| Product type             | Products                                    | Dimension                     | Processes                                   | Deliver Status                                                       |
| Plates / Sheets          | Plates / Sheets                             | 0.08-200mm(T)*W*L             | Forging, hot rolling and cold rolling       | Annealed, Solution and<br>Aging, Q+T, ACID-<br>WASHED, Shot Blasting |
| Steel Bar                | Round Bar, Flat Bar,<br>Square Bar          | Ф8-1200mm*L                   | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning,<br>Shot Blasting,                              |
| Coil / Strip             | Steel Coil /Steel Strip                     | 0.03-16.0x1200mm              | Cold-Rolled & Hot-<br>Rolled                | Annealed, Solution and<br>Aging, Q+T, ACID-<br>WASHED, Shot Blasting |
| Pipes / Tubes            | Seamless Pipes/Tubes,<br>Welded Pipes/Tubes | OD:6-219mm x<br>WT:0.5-20.0mm | Hot extrusion, Cold<br>Drawn, Welded        | Annealed, Solution and<br>Aging, Q+T, ACID-<br>WASHED                |

## We can produce Special Alloy the specifications follows:

Note:

(1) listed in the table apex diameter (d), to steel thickness (a) multiples said.

(2) in the ASTM A6 standard specified scope can meet any additional conditions.

(3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar: Diameter: 1mm-2000mm Square bar: Size: 50mm \* 50mm-600mm \*600mm Plate steel/flat bar: Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm Tube/pipe: Size: OD: 6-219mm WT: 1-35 mm. Cold-rolled sheet: Thickness: 2-5mm Width: 1000mm Length: 2000mm Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm Length: We can supply any length based on the customer's requirement. Forging/hot rolling/ extrusion of steel. Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement.



UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price. We serve you with our honesty, integrity, and professionality.